

## Polyurethane Finish

**PRODUCT DESCRIPTION** A two component solvent borne, high solids aliphatic acrylic polyurethane topcoat with optimised application properties and superior aesthetics.

**INTENDED USES** As a cosmetic finish on above water areas. Suitable for use on topsides, external superstructure, external decks and boottops. For use at Newbuilding, Maintenance & Repair or On Board Maintenance.

<b>PRODUCT INFORMATION</b>	<b>Colour</b>	RUB000-White, RUY999-Black and a wide range of colours.
	<b>Finish/Sheen</b>	High Gloss
	<b>Part B (Curing Agent)</b>	RUA046
	<b>Volume Solids</b>	70% ±3% (ISO 3233:1998)
	<b>Mix Ratio</b>	8 volume(s) Part A to 1 volume(s) Part B
	<b>Typical Film Thickness</b>	50 microns dry (71 microns wet). Range 50 - 75 microns dry (71 - 107 microns wet) may be specified depending upon end use.
	<b>Theoretical Coverage</b>	14 m <sup>2</sup> /litre at 50 microns dft, allow appropriate loss factors
	<b>Method of Application</b>	Airless Spray, Brush, Conventional Spray, Roller
	<b>Flash Point (Typical)</b>	Part A 26°C; Part B 49°C; Mixed 29°C
	<b>Induction Period</b>	Not required

<b>Drying Information</b>	-5°C	5°C	25°C	35°C				
Touch Dry [ISO 9117/3:2010]	22 hrs	6 hrs	2 hrs	90 mins				
Hard Dry [ISO 9117-1:2009]	68 hrs	24 hrs	6 hrs	4 hrs				
Pot Life	3 hrs	2.5 hrs	1.5 hrs	60 mins				
<b>Overcoating Data - see limitations</b>	<b>Substrate Temperature</b>							
	-5°C		5°C		25°C		35°C	
<b>Overcoated By</b>	Min	Max	Min	Max	Min	Max	Min	Max
Interthane 990E	60 hrs	ext	21 hrs	ext	6 hrs	ext	4 hrs	ext

<b>REGULATORY DATA</b>	<b>VOC</b>	310 g/lit as supplied (EPA Method 24)
		207 g/kg (Top Coat) of liquid paint as supplied. EU Solvent Emissions Directive (Council Directive 1999/13/EC)
		284 g/lit Chinese National Standard GB23985
		303 g/lit in accordance with Korea Clean Air Conservation Act
		<b>Note:</b> VOC values are typical and are provided for guidance purposes only. These may be subject to variation depending on factors such as differences in colour and normal manufacturing tolerances.

## Polyurethane Finish

### CERTIFICATION

When used as part of an approved scheme, this material has the following certification:

- Fire Resistance - Surface Spread of Flame (Exova Warringtonfire)
- Fire Resistance - Smoke & Toxicity (Exova Warringtonfire)
- NORSOK M-501, Rev 6, system no.1 (Norer)
- Fire Resistance - Marine Equipment Directive compliant

Approvals issued by external bodies may be dependent upon formulation and/ or manufacturing site. Consult your International Paint representative for details.

---

### SYSTEMS AND COMPATIBILITY

Interthane 990E must be applied over a recommended primer system, which will vary depending upon the vessel area. Direct application is acceptable over the following marine anticorrosives:

Intergard 264 (USA)  
Intergard 5600  
Intergard 7500  
Intergard 7600  
Intershield 300  
Intershield 300HS  
Intershield 803  
Intershield One-2-One  
Interstores Alkyd Primer

A tiecoat of Intergard 263, Intergard 267 or Intergard 269 may be required if Interthane 990E is to be applied over other epoxy primers and may also be used to extend the maximum overcoating interval when Interthane 990E is to be applied over those primers listed above.

Interprime 198 may also be used as a primer for Interthane 990E.

Consult your local representative for the system best suited for the surfaces to be protected.

---

### SURFACE PREPARATIONS

Use in accordance with standard Worldwide Marine Specifications.

All surfaces to be coated should be clean, dry and free from contamination.

High pressure fresh water wash or fresh water wash, as appropriate, and remove all oil or grease, soluble contaminants and other foreign matter in accordance with SSPC-SP1 solvent cleaning.

#### NEWBUILDING/MAJOR REFURBISHMENT

Interthane 990E should always be applied over a recommended primer coating scheme. The primer surface should be dry and free from all contamination, and Interthane 990E must be applied within the overcoating intervals specified (consult the relevant product data sheet). For boottop areas the overcoating intervals for primers are reduced. Consult International Paint.

Areas of breakdown, damage etc. should be prepared to the specified standard (eg. Sa2½ (ISO 8501-1:2007)) and primed prior to the application of Interthane 990E.

#### REPAIR/OBM

Interthane 990E should always be applied over a recommended primer coating scheme. The primer surface should be dry and free from all contamination, and Interthane 990E must be applied within the overcoating intervals specified (consult the relevant product data sheet). For boottop areas the overcoating intervals for primers are reduced. Consult International Paint.

Areas of breakdown, damage etc. should be prepared to the specified standard (eg. Sa2½ (ISO 8501-1:2007)) and primed prior to the application of Interthane 990E.

Interthane 990E may be applied directly over aged Interthane 990E following thorough fresh water washing and degreasing provided the coating to be overcoated is in an intact and tightly adherent condition. Loose or flaking coatings should be removed back to a firm edge and Interthane 990E or an appropriate primer should be used to repair the area before application of the full coat.

This product may be applied directly over most generic types of paint that have been aged for at least 3 months. It is advisable that a small trial be carried out before applying a full coat.

Consult your local representative for specific recommendations.

#### NOTE

**For use in Marine situations in North America, the following surface preparation standards can be used: SSPC-SP10 in place of Sa2½ (ISO 8501-1:2007)**

## Polyurethane Finish

### APPLICATION

<b>Mixing</b>	Material is supplied in 2 containers as a unit. Always mix a complete unit in the proportions supplied. Once the unit has been mixed it must be used within the working pot life specified. (1) Agitate Base (Part A) with a power agitator. (2) Combine entire contents of Curing Agent (Part B) with Base (Part A) and mix thoroughly with power agitator.
<b>Thinner</b>	Consult the local representative for advice during application in extreme conditions. Do not thin more than allowed by local environmental legislation.
<b>Airless Spray</b>	Tip Range 0.33-0.45 mm (13-18 thou) Total output fluid pressure at spray tip not less than 155 kg/cm <sup>2</sup> (2200 p.s.i.)
<b>Conventional Spray</b>	Use suitable proprietary equipment. Thinning may be required.
<b>Brush</b>	Suitable.
<b>Roller</b>	Suitable.
<b>Cleaner</b>	International GTA056/GTA713/GTA733. Choice of cleaner maybe subject to local legislation. Please consult your local representative for specific advice.
<b>Work Stoppages and Cleanup</b>	Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with International GTA713. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units. Clean all equipment immediately after use with International GTA056/GTA713/GTA733. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays. Do not exceed pot life limitations. All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.
<b>Welding</b>	In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation. In North America do so in accordance with instruction in ANSI/ASC Z49.1 "Safety in Welding and Cutting."

### SAFETY

**All work involving the application and use of this product should be performed in compliance with all relevant national Health, Safety & Environmental standards and regulations.**

**Prior to use, obtain, consult and follow the Material Safety Data Sheet for this product concerning health and safety information. Read and follow all precautionary notices on the Material Safety Data Sheet and container labels. If you do not fully understand these warnings and instructions or if you can not strictly comply with them, do not use this product. Proper ventilation and protective measures must be provided during application and drying to keep solvent vapour concentrations within safe limits and to protect against toxic or oxygen deficient hazards. Take precautions to avoid skin and eye contact (ie. gloves, goggles, face masks, barrier creams etc.) Actual safety measures are dependant on application methods and work environment.**

#### **EMERGENCY CONTACT NUMBERS:**

**USA/Canada - Medical Advisory Number 1-800-854-6813**

**Europe - Contact (44) 191 4696111. For advice to Doctors & Hospitals only contact (44) 207 6359191**

**China – Contact (86) 532 83889090**

**R.O.W. - Contact Regional Office**

**Warning: Contains isocyanate. Wear air-fed hood for spray application.**

## Polyurethane Finish

### LIMITATIONS

This product is not recommended for use in immersed conditions.

Interthane 990E may be used on boottop areas at reduced overcoating intervals over appropriate primers. Consult International Paint.

For brush and roller application, and in some colours, two coats of Interthane 990E may be required to give uniform coverage, especially when applying Interthane 990E over dark undercoats and when using certain lead-free bright finish colours such as yellows and oranges. Best practice is to use a colour compatible intermediate or anticorrosive coating under Interthane 990E. Care should be exercised to avoid the application of dry film thicknesses in excess of 100 microns (4 mils).

Low temperature, high relative humidity and condensation occurring during or immediately after application may result in a matt finish and an inferior film. Premature exposure to ponding water will cause colour change, especially in dark colours and at low temperatures.

Maximum dry temperature resistance; 120°C (248°F). Please contact AkzoNobel for advice on chemical resistance, Overcoating information is given for guidance only and is subject to regional variation depending upon local climate and environmental conditions. Consult your local International Paint representative for specific recommendations. Apply in good weather. Temperature of the surface to be coated must be at least 3°C above the dew point. For optimum application properties bring the material to 21-27°C, unless specifically instructed otherwise, prior to mixing and application. Unmixed material (in closed containers) should be maintained in protected storage in accordance with information given in the STORAGE Section of this data sheet. Technical and application data herein is for the purpose of establishing a general guideline of the coating application procedures. Test performance results were obtained in a controlled laboratory environment and International Paint makes no claim that the exhibited published test results, or any other tests, accurately represent results found in all field environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection, verification of performance and use of the coating.

In the overcoating data section 'ext' = extended overcoating period. Please refer to our Marine Painting Guide - Definitions and Abbreviations available on our website.

UNIT SIZE	Unit Size	Part A		Part B	
		Vol	Pack	Vol	Pack
	20 lt	17.78 lt	20 lt	2.22 lt	5 lt
	5 lt	4.45 lt	5 lt	0.55 lt	1 lt

For availability of other unit sizes consult International Paint

UNIT SHIPPING WEIGHT (TYPICAL)	Unit Size	Unit Weight
	20 lt	27.2 Kg
	5 lt	8.01 Kg

STORAGE	Shelf Life	Part A - 12 months minimum at 25°C. Part B - 18 months minimum at 25°C Subject to reinspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.

**WORLDWIDE AVAILABILITY** Consult International Paint.

### IMPORTANT NOTE

*The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local representative that this data sheet is current prior to using the product.*

*This Technical Data Sheet is available on our website at [www.international-marine.com](http://www.international-marine.com) or [www.international-pc.com](http://www.international-pc.com), and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.*

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies.

© AkzoNobel, 2024

[www.international-marine.com](http://www.international-marine.com)